


Applications

- Automotive electronics
- Industrial electronics
- Home appliances

Features

- For temperature measurement up to 300 °C and 350 °C respectively
- Mechanically reinforced by rugged ceramic disk
- High stability when subjected to heat cycling and aggressive environment
- Leads: dumet wires (copper-clad FeNi)



Dimensions
in mm

Delivery mode

Bulk

Climatic category (IEC 60068-1)		55/300/56	
Resistance tolerance	$\Delta R_N/R_N$	$\pm 3\%$, $\pm 5\%$	
Dissipation factor (in air)	δ_{th}	approx. 1,5	mW/K
Thermal cooling time constant (in air)	τ_c	approx. 18	s

R_{25}	R_{TN}	T_N	No. of R/T characteristic	$B_{0/100}$	$B_{25/85}$	Ordering code
Ω	Ω	°C		K	K	
2,2 k	6 k	0	8401	$3390 \pm 2\%$	3420	B57660G0222+000
5,4 k	15 k	0	8402	$3450 \pm 2\%$	3480	B57660G0542+000
10,7 k	30 k	0	8407	$3450 \pm 2\%$	3480	B57660G0113+000
49,1 k	3,3 k	100	8403	$3970 \pm 2\%$	3992	B57660G0493+000
98,6 k	0,55 k	200	8404	$4300 \pm 3\%$ ¹⁾	4066	B57660G0993+000
231,4 k	1 k	200	8405	$4537 \pm 3\%$ ¹⁾	4240	B57660G0234+000 ³⁾
1388,1 k	4 k	200	8406	$5133 \pm 3\%$ ²⁾	4557	B57660G0145+000 ³⁾

+ : H for $\Delta R_N/R_N = \pm 3\%$
 J for $\Delta R_N/R_N = \pm 5\%$

1) $B_{100/200}$

2) $B_{200/300}$

3) for $T_{max} = 350\text{ °C}$

Reliability data

Test	Standard	Test conditions	$\Delta R_{25}/R_{25}$ (typical)	Remarks
Storage in dry heat	IEC 60068-2-2	Storage at upper category temperature T: 300 °C t: 1000 h	< 3 %	No visible damage
Storage in damp heat, steady state	IEC 60068-2-3	Temperature of air: 85 °C Relative humidity of air: 85 % Duration: 56 days	< 2 %	No visible damage
Rapid temperature cycling	IEC 60068-2-14	Lower test temperature: – 55 °C Upper test temperature: 200 °C Number of cycles: 1000	< 2 %	No visible damage

Herausgegeben von EPCOS AG

Unternehmenskommunikation, Postfach 80 17 09, 81617 München, DEUTSCHLAND

☎ ++49 89 636 09, FAX (0 89) 636-2 26 89

© EPCOS AG 2002. Vervielfältigung, Veröffentlichung, Verbreitung und Verwertung dieser Broschüre und ihres Inhalts ohne ausdrückliche Genehmigung der EPCOS AG nicht gestattet.

Bestellungen unterliegen den vom ZVEI empfohlenen Allgemeinen Lieferbedingungen für Erzeugnisse und Leistungen der Elektroindustrie, soweit nichts anderes vereinbart wird.

Diese Broschüre ersetzt die vorige Ausgabe.

Fragen über Technik, Preise und Liefermöglichkeiten richten Sie bitte an den Ihnen nächstgelegenen Vertrieb der EPCOS AG oder an unsere Vertriebsgesellschaften im Ausland. Bauelemente können aufgrund technischer Erfordernisse Gefahrstoffe enthalten. Auskünfte darüber bitten wir unter Angabe des betreffenden Typs ebenfalls über die zuständige Vertriebsgesellschaft einzuholen.

Published by EPCOS AG

Corporate Communications, P.O. Box 80 17 09, 81617 Munich, GERMANY

☎ ++49 89 636 09, FAX (0 89) 636-2 26 89

© EPCOS AG 2002. Reproduction, publication and dissemination of this brochure and the information contained therein without EPCOS' prior express consent is prohibited.

Purchase orders are subject to the General Conditions for the Supply of Products and Services of the Electrical and Electronics Industry recommended by the ZVEI (German Electrical and Electronic Manufacturers' Association), unless otherwise agreed.

This brochure replaces the previous edition.

For questions on technology, prices and delivery please contact the Sales Offices of EPCOS AG or the international Representatives.

Due to technical requirements components may contain dangerous substances. For information on the type in question please also contact one of our Sales Offices.