

Ferrite Polymer Composites

General Information

Ferrite cores are familiar as brittle, rigid and bulky components for high-inductance coils and transformers. The performance of such ferrites depends very much on external influences such as temperature, pressure, electromagnetic fields and frequency.

FPC is a homogeneous mixture of ferrite powder and plastic with outstanding mechanical and magnetic properties. This rugged material can be processed into injection-molded parts or thin, flexible film to open up innovative applications.

The new C351 film is suitable for high-temperature applications up to 200 °C and is UL 94-V0-listed. It is also available with copper coatings of 35 to 75 µm and in various thicknesses from 0,2 to 0,4 mm. FPC film of materials C350 and C351 can also be supplied in self-adhesive versions.

FPC film is ideal for EMC applications, e.g. to shield coils against metals or absorb interference at frequencies of 500 MHz and higher. It opens up many other applications, such as implementation of low-profile coils for identification systems and electronic article surveillance in retailing and logistics, for sensors or contactless smart cards. FPC can also be used for compensation of deflection yoke coils in TV picture tubes and computer monitors. This innovative material is also suitable as spacing between ferrite cores – instead of air gaps or non-magnetic films – to suppress leakage fields, for instance, or to adjust the biasing curve.

Basic features

- Composite material of polymer and ferrite for injection molded parts
- Minor influence of temperature
- High dc magnetic bias capability
- Suitable for a wide frequency range
- High electrical resistance

Technical benefits

- High mechanical stability
- Excellent dimensional stability
- Manufacturing technique: injection molding
→ production of any core shape possible
- Distributed air gap → low winding losses

Applications

- Inductive proximity switches
- Identification systems, e.g. immobilizer in automobiles
- Non-contact power transmission
- Resonance inductors for DC/DC converters

Core shapes on request

Physical properties

Material	Symbol	Unit	C302
Initial permeability; $f = 1 \text{ MHz}$	μ_i		$17 \pm 20 \%$
Flux density (near saturation) $H = 25 \text{ kA/m}; f = 10 \text{ kHz}$	$B_S (25^\circ \text{C})$	mT	330
Remanent flux density $H = 25 \text{ kA/m}; f = 10 \text{ kHz}$	$B_r (25^\circ \text{C})$	mT	15
Coercive field strength $H = 25 \text{ kA/m}; f = 10 \text{ kHz}$	$H_C (25^\circ \text{C})$	A/m	770
Relative loss factor $f = 1 \text{ MHz}$ $f = 100 \text{ MHz}$	$\tan \delta / \mu_i$		$< 0,0004$ $< 0,03$
Hysteresis material constant	η_B	$10^{-3}/\text{mT}$	$< 0,25$
Temperature coefficient	$\alpha = \Delta \mu / \mu \Delta T$	1/K	$< 0,0002$
Density		kg/m^3	3500
Resistivity $f = 10 \text{ kHz}$ $f = 10 \text{ MHz}$	ρ	Ωm	21 13
Dielectric constant $f = 10 \text{ kHz}$ $f = 10 \text{ MHz}$	ϵ_r		280 100
Max. operating temperature	T_{max}	$^\circ \text{C}$	180

Basic features

- FPC is a composite material of polymer and ferrite
- FPC film is a thin, mechanically flexible film

Technical benefits

- Stable magnetic characteristics
- Low weight: FPC film is 40% lower in density than ferrite
- High mechanical strength
- Shaping as required: customer-specific solutions possible
- Economy: easy transport and storage, simple, rationalized processing, low mounting volume
- C351 film suitable for high-temperature applications (up to 200 °C)
- Material C351 approved to UL 94-V0 (E 140 693)
- Various film thickness (from 0,2 to 0,4 mm)
- Self-adhesive versions
- C351 film with optional copper coatings 35 to 75 µm thick

Applications

- Implementation of low-profile coils, e.g. for
 - identification systems
 - security tags for electronic article surveillance
 - sensors
 - inductive reading of smart cards
- Electromagnetic shielding of coils from metals to prevent interference
- EMC: absorption of radiated emissions at frequencies ≥ 500 MHz
- Compensation of deflection yokes to correct distortion at the corners of TV screens and monitors
- Spacing between ferrite cores (as a substitute for air gaps or non-magnetic films) for
 - suppression of the leakage field
 - adjustment of the biasing curve

FPC Film	
C 350, C 351	B68450 ... B68452

Ordering details

The ordering codes are structured as follows:

1st group Design	2nd group Film thickness/width		3rd group Copper coating ¹⁾ /material	
B68450: Film on reel	A: 0,2 mm B: 0,3 mm	0080: 80 mm	X: Default letter	350 351
B68451: Film on reel, self-adhesive	C: 0,4 mm			
B68452: Film on reel, copper-coated (only in combination with C351!)			A: 35 µm B: 50 µm C: 75 µm	351

Material	Thickness (mm)	Extra features	Ordering code
C350	0,2		B68450-A0080-X350
C351	0,2		B68450-A0080-X351
C350	0,2	self-adhesive	B68451-A0080-X350
C350	0,2		B68451-A0080-X350
C351	0,3	self-adhesive	B68451-B0080-X351
C351	0,3		B68451-B0080-X351
C351	0,2	copper-coated	B68452-A0080-X351
C351	0,2		B68452-A0080-X351

FPC film is supplied in units of 50 m length.

¹⁾ Copper coating only in combination with C351.

Physical properties (material values defined on 0,2 mm thick film)

Material	Symbol	Unit	C350	C351 ³⁾
Initial permeability ¹⁾ $f = 1 \text{ MHz}$	μ_i		$9 \pm 20 \%$	$9 \pm 20 \%$
Flux density (near saturation) ¹⁾ $H = 25 \text{ kA/m}$ $f = 10 \text{ kHz}$	B_S	mT	255	255
Remanent flux density ¹⁾ $H = 25 \text{ kA/m}$ $f = 10 \text{ kHz}$	B_r	mT	9	9
Coercive field strength ¹⁾ $H = 25 \text{ kA/m}$ $f = 10 \text{ kHz}$	H_C	A/m	600	600
Relative loss factor ¹⁾ $f = 10 \text{ MHz}$ $f = 1 \text{ GHz}$	$\tan\delta/\mu_i$		$< 0,005$ $< 0,400$	$< 0,005$ $< 0,400$
Hysteresis material constant	η_B	$10^{-3}/\text{mT}$	< 2	< 2
Temperature coefficient ¹⁾	$\alpha = \Delta\mu/\mu\Delta T$	1/K	$< 5 \cdot 10^{-5}$	$< 5 \cdot 10^{-5}$
Density		kg/m ³	2930	2930
Resistivity ¹⁾ $f = 1 \text{ kHz}$ $f = 10 \text{ MHz}$	ρ	Ωm	500 100	500 100
Dielectric constant ¹⁾ $f = 1 \text{ kHz}$ $f = 10 \text{ MHz}$	ε_r		700 21	700 21
Dielectric strength		kV/mm	1	0,8
Max. operating temperature	$T_{\max}$	°C	120	200
Tensile strength ²⁾	σ_Z	N/mm ²	1,5	2,5
Tearing resistance ²⁾		%	25	25
Compressibility ²⁾	κ	N/mm ²	70	70

1) $T = 25 \text{ °C}$ in accordance with IEC 51 (CO) 282

2) $T = 23 \text{ °C}$ and 50 % r.h.

3) UL 94, flame class V0 (listed E 140 693)

Herausgegeben von EPCOS AG

Marketing Kommunikation, Postfach 80 17 09, 81617 München, DEUTSCHLAND

© EPCOS AG 2000. Alle Rechte vorbehalten. Vervielfältigung, Veröffentlichung, Verbreitung und Verwertung dieser Broschüre und ihres Inhalts ohne ausdrückliche Genehmigung der EPCOS AG nicht gestattet.

Mit den Angaben in dieser Broschüre werden die Bauelemente spezifiziert, keine Eigenschaften zugesichert. Bestellungen unterliegen den vom ZVEI empfohlenen Allgemeinen Lieferbedingungen für Erzeugnisse und Leistungen der Elektroindustrie, soweit nichts anderes vereinbart wird.

Diese Broschüre ersetzt die vorige Ausgabe.

Fragen über Technik, Preise und Liefermöglichkeiten richten Sie bitte an den Ihnen nächstgelegenen Vertrieb der EPCOS AG oder an unsere Vertriebsgesellschaften im Ausland.

Bauelemente können aufgrund technischer Erfordernisse Gefahrstoffe enthalten. Auskünfte darüber bitten wir unter Angabe des betreffenden Typs ebenfalls über die zuständige Vertriebsgesellschaft einzuholen.

Published by EPCOS AG

Marketing Communications, P.O. Box 80 17 09, 81617 Munich, GERMANY

© EPCOS AG 2000. All Rights Reserved. Reproduction, publication and dissemination of this brochure and the information contained therein without EPCOS' prior express consent is prohibited.

The information contained in this brochure describes the type of component and shall not be considered as guaranteed characteristics. Purchase orders are subject to the General Conditions for the Supply of Products and Services of the Electrical and Electronics Industry recommended by the ZVEI (German Electrical and Electronic Manufacturers' Association), unless otherwise agreed.

This brochure replaces the previous edition.

For questions on technology, prices and delivery please contact the Sales Offices of EPCOS AG or the international Representatives.

Due to technical requirements components may contain dangerous substances. For information on the type in question please also contact one of our Sales Offices.