

# DATA SHEET

**PTS30/19/I**  
PT, PTS, PTS/I cores and  
accessories


Supersedes data of September 2004

2008 Sep 01

## CORE SETS

## Effective core parameters

SYMBOL	PARAMETER	VALUE	UNIT
$\Sigma(l/A)$	core factor (C1)	0.412	mm <sup>-1</sup>
$V_e$	effective volume	5940	mm <sup>3</sup>
$l_e$	effective length	49.5	mm
$A_e$	effective area	120	mm <sup>2</sup>
$A_{min}$	minimum area	111	mm <sup>2</sup>
$m$	mass of set	≈ 31	g



## Core sets for general purpose transformers and power applications

Clamping force for  $A_L$  measurements,  $60 \pm 20$  N.

GRADE	$A_L$ (nH)	$\mu_e$	AIR GAP ( $\mu$ m)	TYPE NUMBER
3C92 des	$3830 \pm 25 \%$	≈ 1260	≈ 0	PTS30/19/I-3C92
3C94	$5400 \pm 25 \%$	≈ 1770	≈ 0	PTS30/19/I-3C94
3C96 des	$4840 \pm 25 \%$	≈ 1590	≈ 0	PTS30/19/I-3C96

## Properties of core sets under power conditions

GRADE	B (mT) at	CORE LOSS (W) at		
	H = 250 A/m; f = 25 kHz; T = 100 °C	f = 100 kHz; $\hat{B}$ = 100 mT; T = 100 °C	f = 100 kHz; $\hat{B}$ = 200 mT; T = 100 °C	f = 500 kHz; $\hat{B}$ = 50 mT; T = 100 °C
3C92	≥ 320	≤ 0.53	≤ 3.5	—
3C94	≥ 320	≤ 0.53	≤ 3.5	—
3C96	≥ 315	≤ 0.4	≤ 2.7	≤ 2.2

## BOBBINS AND ACCESSORIES

For coil formers, winding data and mounting parts, see data sheet, "P30/19".

## PT, PTS, PTS/I cores and accessories

PTS30/19/I




## DATA SHEET STATUS DEFINITIONS

DATA SHEET STATUS	PRODUCT STATUS	DEFINITIONS
Preliminary specification	Development	This data sheet contains preliminary data. Ferroxcube reserves the right to make changes at any time without notice in order to improve design and supply the best possible product.
Product specification	Production	This data sheet contains final specifications. Ferroxcube reserves the right to make changes at any time without notice in order to improve design and supply the best possible product.

## DISCLAIMER

**Life support applications** — These products are not designed for use in life support appliances, devices, or systems where malfunction of these products can reasonably be expected to result in personal injury. Ferroxcube customers using or selling these products for use in such applications do so at their own risk and agree to fully indemnify Ferroxcube for any damages resulting from such application.

## PRODUCT STATUS DEFINITIONS

STATUS	INDICATION	DEFINITION
Prototype		These are products that have been made as development samples for the purposes of technical evaluation only. The data for these types is provisional and is subject to change.
Design-in		These products are recommended for new designs.
Preferred		These products are recommended for use in current designs and are available via our sales channels.
Support		These products are <b>not</b> recommended for new designs and may not be available through all of our sales channels. Customers are advised to check for availability.