

## SFSH4.5MCB

Ceramic Filter

### 1. SCOPE

(范围)

This specification is applied to the ceramics filter used for TV/VCR

(本规格书适用于电视机/录像机用陶瓷滤波器)


### 2. MODEL NAME

(产品名称)

| Part No. (产品号) | Customer`s Part No.(顾客产品号) | Drawing No.(图号) |
|----------------|----------------------------|-----------------|
| SFSH4.5MCB     | /                          | JYD-062         |

### 3. DIMENSIONS

(尺寸)



- ① Input(输入)
- ② Ground(接地)
- ③ Output(输出)

### Materials(材料)

| Terminal(端子) | Sn plated on Cu (铜镀锡) |
|--------------|-----------------------|
| Coating(涂料)  | Epoxy Resin(环氧树脂)     |

Unit(单位): mm





Ceramic Filter

#### 4. ELECTRICAL CHARACTERISTICS


(电气性能)

| ` " " | (七 (江北)  |   |  |  |
|-------|--|---|--|--|
|       | Item<br>(项目)   | Requirements<br>(要求)  |  |  |
| 1     | Center Frequency of 3 dB Bandwidth (fo) (3 dB 带宽的中心频率) | 4.490~4.540MHZ  |  |  |
| 2     | 3 dB Bandwidth<br>(3dB 带宽)                             | ±70KHZ  |  |  |
| 3     | 20dB Bandwidth<br>(20dB 带宽)                            | 600Khz (max)  |  |  |
| 4     | Insertion Loss (插入损耗) At minimum loss point (最小损耗点)    | 6.0 dB (max)  |  |  |
| 5     | Ripple(带内波动)<br>Within 3 dB Bandwidth(3 dB 带宽内)        | 1.0 dB ( max)   |  |  |
| 6     | Spurious Response<br>(阻带衰耗)                            | 0~4.5MHz: 30dB (min)<br>4.5~7MHz: 15dB (min)<br>7~10MHz: 30dB (min) |  |  |
| 7     | Insulation Resistance<br>(绝缘阻抗)                        | 100M Ω min (D.C. 100V)  |  |  |
| 8     | Withstanding Voltage<br>(耐电压)                          | D.C. 50V, 1 Min (max)   |  |  |
| 9     | Storage Temp. Range<br>(贮存温度范围)                        | -40°C~+85°C   |  |  |
| 10    | Test Temp.&Humi.Condition (测试温、湿度条件)                   | +10°C~+30°C、40%~80%   |  |  |
| 11    | Input /Output Impedance<br>(输入、输出阻抗)                   | 1000 Ω  |  |  |

### 5. TEST CIRCUIT

(测试电路)

Unless any necessity to measure under a standard condition(Temp: $20\pm2^{\circ}$ C.Humi.: $65\pm5\%$ )is occurred.( 必要时标准测量条件为温度  $20\pm\ 2^{\circ}$ 、相对湿度  $65\pm\ 5\%$ )





# SFSH4.5MCB

Ceramic Filter

### 6. PHYSICAL AND ENVIRONMENTAL CHARACTERISTICS

(物理及环境特性)

|   | Test Item   | Condition of Test  | Requirements   |
|---|---|--|--|
|   | (试验项目)  | (试验条件)   | (要求)   |
|   | Lead Strength<br>(引脚强度)<br>Lead Pulling   | Force of 0.5kg is applied to each lead in axial direction for 10sec (沿每个引脚轴向施加 0.5kg 力保持 10 秒钟) When force of 0.25kg is applied to each lead in axial  | No mechanical damage and the measured values                               |
| 1 | (引脚拉力)<br>Lead Bending<br>(引脚弯曲)  | direction.the lead shall folded up to 90° from the axial direction and folded back to the axial direction. (沿引脚轴向施加 0.25kg 力的时候把引脚折弯 90 度后再折回原形)   | shall meet Table<br>1.(无机械损伤,<br>测量值满足表 1<br>要求)                           |
| 2 | Solderability<br>(可焊性)  | Lead terminals are immersed in resin for 5 seconds and then immersing in a soldering bath(235±5℃)for 5±0.5sec.(引脚在助剂内浸 5 秒后再浸入 235±5℃ 的锡炉内 5±0.5 秒)  | The solder shall coat at least 90% of the surface of terminal(引脚上锡覆盖率≥90%) |
| 3 | Storage in High<br>Temp.<br>(高温贮存)  | After being placed in a chamber with 85℃ for 100 hours and then being placed in natural condition for 1 hours, then measure.(85℃环境下存放 100 小时后取出自然存放 1 小时测试)  |  |
| 4 | Storage in Low<br>Temp.<br>(低温贮存)   | After being placed in a chamber with -25℃ for 100 hours and then being placed in natural condition for 1 hours, then measure.(-25℃环境下存放 100 小时后取出自然存放 1 小时测试)  |  |
| 5 | Humidity<br>(潮湿)  | After being placed in a chamber (Humi.:90~95%RH,Temp.:40±2℃) for 100 hours and then being placed in natural condition for 1 hours, then measure. (温度 40±2℃;湿度 90~95%的环境下存放 100 小时后取出自然存放 1 小时测试)   | The measured value shall meet Table 1(测量值满                                 |
| 6 | After temperature cycling of -55 ℃(30 minutes)to +85 ℃(30 minutes)was performed 5 times,Resonator shall be measured after being placed in natural condition for 1 hour(-55 ℃下 30 分钟到+85 ℃下 30 分钟循环 5 次后自然存放 1 小时测量) |  | 足衣 1 安水)   |
| 7 | Resistance to<br>soldering Heat<br>(耐焊接热)   | Lead terminals are immersed up to 2.0 mm from the root of terminals in solder bath of 265±5℃ for 10±1seconds, Resonator shall be measured after being placed in natural condition for 1 hour.(引脚距根部 2mm 以下浸入 265±5℃的锡炉中 10±1 秒取出自然存放 1 小时测量) |  |



### SFSH4.5MCB

Ceramic Filter

### 续上表:

| 8  | Random Drop<br>(自由跌落)              | Filter shall be measured after 3 times random dropping from the hight of 1 m to concrete floor.(滤 波器从 1 米高向水泥地板自由跌落 3 次后测量)  | The measured                                    |
|----|------------------------------------|--|---|
| 9  | Vibration<br>(振动)                  | Filter shall be measured after being applied vibration as below:(滤波器做如下振动后测量) Vibration Freq.(振动频率): 10 Hz to 55 Hz Amplitude(幅度): 1.5mm Directions(方向): 3 axial directions(三轴向) Time(时间): 1 hour/each direction(1 小时/向) | value shall meet Table 1(测量值满 足表 1 要求)          |
| 10 | Temperature characteristics (温度特性) | Filter shall be measured within −25℃ to +85℃ temperature range. Temp. coefficient of Fo (滤波器 在−25℃至+85℃温度范围内测量 Fo 的温度系数)   | ≤100ppm/℃<br>Reference temp.<br>(参考温度):<br>+20℃ |

### Table 1(表 1)

| 14010 1(40 1)               |             |  |
|-----------------------------|-------------|--|
| Item                        | Limit Value |  |
| (项目)                        | (限定值)       |  |
| 3 dB Bandwidth<br>(3dB 带宽)  | ±20kHz max  |  |
| 20dB Bandwidth<br>(20dB 带宽) | ±30kHz max  |  |
| Insertion Loss<br>(插入损耗)    | ±2.0 dB max |  |

\* Note: The limits in the above table are referenced to the initial measurements.

(上表中的限定值参照初始测量值)

### 7. NOTICE

(注意)

- 1. Do not use this product with bend. The component may be damaged if excess Mechanical stress is applied to it mounted on the printed circuit board. (本产品不能折弯使用,在电路板安装时使用过大的机械压力可能造成产品损坏。)
- 2. This specification limits the quality of the component as a single Unit Please make sure that the component is evaluated and confirmed the drawing When it is mounted to your product. (本规格书只规定了部件本身的品质,应用于您的产品时请确认图纸该产品是否适用。)