

## ROITHNER LASERTECHNIK GIRDH

WIEDNER HAUPTSTRASSE 76 IO40 VIENNA AUSTRIA TEL. +43 I 586 52 43 -0, FAX. -44, OFFICE@ROITHNER-LASER.COM



# LED19FC-TEC

#### **TECHNICAL DATA**



# Mid-Infrared Light Emitting Diode, Flip-Chip Design

Light Emitting Diodes with central wavelength 1.95 µm series are based on heterostructures grown on GaSb substrates by LPE. Solid solutions AlGaAsSb are used in the active layer. Wide band gap solid solutions AlGaAsSb with Al content 64% are used for good electron confinement. LED19FC-TEC has a stable ouput power and a lifetime more then 80000 hours.


#### **Features**

- Structure: GalnAsSb/AlGaAsSb, Flip-Chip Design
- Peak Wavelength: typ. 1.95 μm
- Optical Ouput Power: typ. 1.0 mW qCW
- Package: TO-5, with TEC, thermistor and window




### **Specifications**

Item	Condition	Rating			Unit
ILCIII	Condition	Min.	Тур.	Max.	o i i i
Peak Wavelength	T=300 K	1.90	1.95	1.99	μm
FWHM	150 mA CW	100	150	200	nm
Quasi-CW Optical Power	200 mA qCW	0.8	1.0	1.4	mW
Pulsed Optical Power	1 A	20	25	35	mW
Switching Time	T=300 K	10	20	30	ns
Operation Voltage	200 mA qCW				V
Operating Temperature	-240 +50				ç
Emitting Area	670x770				μm
Soldering Temperature	180				ပ္
Package	TO-5, with built-in thermocooler, thermoresistor, with cap and quartz window				



#### **Operating Regime**



#### Quasi-CW

- Maximum current 220 mA
- Recommended current 150-200mA

#### **Pulsed**

 Maximum current 1 A (puls lenght 500 ns, repetition rate 2kHz)



# ROITHNER LASERTECHNIK GIRDH

**WIEDNER HAUPTSTRASSE 76** 

1040 VIENNA AUSTRIA TEL. +43 I 586 52 43 -0, FAX. -44, OFFICE@ROITHNER-LASER.COM



## **Typical Performance Curves**

