

## Protective Coating



### **OTHER *M-LINE* COATINGS COMPATIBLE WITH GAGEKOTE #1:**

- Gagekote #5
- EpoxyLite #813

### **DESCRIPTION**

Solvent-thinned (toluene) synthetic resin. Often used as a precoat for Gagekote #5, and EpoxyLite #813. Resistant to

moisture and offers a wide operating temperature range. Provides limited mechanical protection. Convenient to use.

### **CHARACTERISTICS**

**Operating Temperature Range:**  
-320° to +850°F [-195° to +455°C].

**Shelf Life:**  
2 years at +75°F [+24°C].

**Cure Requirements:**  
Single coat air dry for 15 minutes at +75°F [+24°C]. Prior to encapsulation by other coatings, air dry 4 hours at +75°F [+24°C] or 30 minutes at +150°F [+65°C] to prevent solvent entrapment.

### **PACKAGING OPTIONS**

**Kits:**  
1 brush-cap bottle [1 oz/30 ml]  
12 brush-cap bottles [1 oz/30 ml each]  
1 bottle [8 oz/240 ml each]