

**DATA SHEET**

# Basic Dielectric Materials

## Bulk Microwave Dielectrics

Skyworks, through its wholly owned subsidiary Trans-Tech, offers a broad range of ceramic materials that are not characterized for resonator applications, but for bulk, miscellaneous shapes, or substrates. Typical applications include patch antenna substrates, matching structures for circulators and isolators, and miscellaneous support structures. Because such applications are non-resonant, temperature coefficient of resonant frequency does not apply. We list the temperature-dependent coefficients of dielectric constant and linear expansion.

The Magnesium Aluminum Titanate (SMAT) and Magnesium Calcium Titanate (MCT) series are notably easier to machine than most microwave ceramics, and may be more suitable for applications requiring precision machining.

D-4, or Corderite, is a very hard ceramic noted for its low temperature coefficient of expansion which approaches the metal alloy Invar. It is not suitable for substrates. It is occasionally used for dielectric resonator supports due to its low dielectric constant and/or low thermal expansion rate.

Temperature-Stable Dielectrics can be found in the *Temperature Stable Materials* catalog. Please call for a catalog.

Bars and rods are available for all material types. Contact us for custom sizes and shapes.

## Basic Dielectrics

Composition and Type Number	Dielectric Constant ( $\epsilon'$ )	Dielectric Loss Tangent ( $E''/\epsilon''$ )	Temperature Coefficient Dielectric Constant ( $^{\circ}\text{C}^{-1}$ ) (Nominal Value)	Temperature Coefficient of Thermal Expansion ( $^{\circ}\text{C}^{-1}$ ) (Nominal Value)	Thermal Conductivity ( $\text{Cal}/\text{cm}^2/\text{cm}/\text{sec}/^{\circ}\text{C}$ ) ( $^{\circ}\text{C}^{-1}$ ) (Nominal Value)	Density ( $\text{G}/\text{cm}^3$ ) (Nominal Value)	Water Absorption (%) (Nominal Value)
D-4 Corderite	4.5 ± 0.2 @ 9.4 GHz	< 0.0002	+55 x 10 <sup>-6</sup>	2.00 x 10 <sup>-6</sup>	0.007	2.45	–
DS-6 Forsterite	6.3 ± 0.3 @ 9.4 GHz	< 0.0002	+107 x 10 <sup>-6</sup>	10.00 x 10 <sup>-6</sup>	0.009	2.89	0.6
D-15 Mg-Ti	15.0 ± 0.5 @ 9.4 GHz	< 0.0002	+98 x 10 <sup>-6</sup>	7.50 x 10 <sup>-6</sup>	0	3.5	–
D-16 Mg-Ti	16.0 ± 0.5 @ 9.4 GHz	< 0.0002	+98 x 10 <sup>-6</sup>	7.50 x 10 <sup>-6</sup>	0.01	3.6	0
D-38 Ba-Ti	37.0 ± 5% @ 6.0 GHz	< 0.0005	-25 x 10 <sup>-6</sup>	9.40 x 10 <sup>-6</sup>	0.01	4.4	0.3
D-50 Ba-Ti	50.0 ± 5% @ 6.0 GHz	< 0.0005	-250 x 10 <sup>-6</sup>	7.50 x 10 <sup>-6</sup>	0.01	4.35	–
D-100 Titania	100.0 ± 5% @ 6.0 GHz	< 0.0010	-575 x 10 <sup>-6</sup>	7.50 x 10 <sup>-6</sup>	0.01	3.9	0.1

## Magnesium Aluminum Titanate

Composition and Type Number	Dielectric Constant ( $\epsilon'$ )	Dielectric Loss Tangent ( $E''/\epsilon''$ )	Temperature Coefficient Dielectric Constant ( $^{\circ}\text{C}^{-1}$ ) (Nominal Value)	Temperature Coefficient of Thermal Expansion ( $^{\circ}\text{C}^{-1}$ ) (Nominal Value)	Thermal Conductivity ( $\text{Cal}/\text{cm}^2/\text{cm}/\text{sec}/^{\circ}\text{C}$ ) ( $^{\circ}\text{C}^{-1}$ ) (Nominal Value)	Density ( $\text{G}/\text{cm}^3$ ) (Nominal Value)	Water Absorption (%) (Nominal Value)
SMAT-9	9.0 ± 0.3 @ 9.4 GHz	<.00015	+100 x 10 <sup>-6</sup>	7.5 x 10 <sup>-6</sup>	0.025	3.46	0.1
SMAT-9.5	9.5 ± 0.3 @ 9.4 GHz	<.00015	+100 x 10 <sup>-6</sup>	7.5 x 10 <sup>-6</sup>	0.025	3.46	0.1
SMAT-10	10.0 ± 0.5 @ 9.4 GHz	<.00015	+100 x 10 <sup>-6</sup>	7.5 x 10 <sup>-6</sup>	0.025	3.46	0.1
SMAT-11	11.0 ± 0.5 @ 9.4 GHz	<.00015	+100 x 10 <sup>-6</sup>	7.5 x 10 <sup>-6</sup>	0.025	3.46	0.1
SMAT-12	12.0 ± 0.5 @ 9.4 GHz	<.00015	+100 x 10 <sup>-6</sup>	7.5 x 10 <sup>-6</sup>	0.025	3.46	0.1
SMAT-13	13.0 ± 0.5 @ 9.4 GHz	<.00015	+100 x 10 <sup>-6</sup>	7.5 x 10 <sup>-6</sup>	0.025	3.46	0.1
SMAT-14	14.0 ± 0.5 @ 9.4 GHz	<.00015	+100 x 10 <sup>-6</sup>	7.5 x 10 <sup>-6</sup>	0.025	3.46	0.1

**Magnesium Calcium Titanate**

Composition and Type Number	Dielectric Constant ( $\epsilon'$ )	Dielectric Loss Tangent ( $\epsilon''/\epsilon'$ )	Temperature Coefficient Dielectric Constant ( $^{\circ}\text{C}^{-1}$ ) (Nominal Value)	Temperature Coefficient of Thermal Expansion ( $^{\circ}\text{C}^{-1}$ ) (Nominal Value)	Thermal Conductivity ( $\text{Cal}/\text{cm}^2/\text{cm}/\text{sec}/^{\circ}\text{C}$ ) ( $^{\circ}\text{C}^{-1}$ ) (Nominal Value)	Density ( $\text{G}/\text{cm}^3$ ) (Nominal Value)	Water Absorption (%) (Nominal Value)
MCT-18	18.0 $\pm$ 3% @ 9.4 GHz	<.0015	-70 x 10 <sup>-6</sup>	8.40 x 10 <sup>-6</sup>	0.01	3.47	0.1
MCT-20	20.0 $\pm$ 5% @ 9.4 GHz	$\leq$ .0004	-130 x 10 <sup>-6</sup>	8.60 x 10 <sup>-6</sup>	0.01	3.5	0.1
MCT-25	25.0 $\pm$ 5% @ 9.4 GHz	<.0015	-245 x 10 <sup>-6</sup>	8.90 x 10 <sup>-6</sup>	0.01	3.54	0.1
MCT-30	30.0 $\pm$ 5% @ 9.4 GHz	$\leq$ .0010	-370 x 10 <sup>-6</sup>	9.20 x 10 <sup>-5</sup>	0.01	3.59	0.1
MCT-40	40.0 $\pm$ 5% @ 6.0 GHz	<.0015	-580 x 10 <sup>-6</sup>	9.50 x 10 <sup>-6</sup>	0.01	3.62	0.1
MCT-50	50.0 $\pm$ 5% @ 6.0 GHz	<.0015	-730 x 10 <sup>-6</sup>	9.70 x 10 <sup>-6</sup>	0.01	3.65	0.1
MCT-55	55.0 $\pm$ 5% @ 6.0 GHz	<.0015	-800 x 10 <sup>-6</sup>	9.80 x 10 <sup>-6</sup>	0.01	3.68	0.1
MCT-70	70.0 $\pm$ 5% @ 6.0 GHz	<.0015	-960 x 10 <sup>-6</sup>	10.0 x 10 <sup>-6</sup>	0.01	3.7	0.1
MCT-85	85.0 $\pm$ 5% @ 6.0 GHz	<.0015	-1070 x 10 <sup>-6</sup>	10.1 x 10 <sup>-6</sup>	0.01	3.75	0.1
MCT-100	100.0 $\pm$ 5% @ 6.0 GHz	<.0015	-1120 x 10 <sup>-6</sup>	10.3 x 10 <sup>-6</sup>	0.01	3.78	0.1
MCT-115	125.0 $\pm$ 5% @ 6.0 GHz	<.0015	-1120 x 10 <sup>-6</sup>	10.4 x 10 <sup>-6</sup>	0.01	3.8	0.1
MCT-125	125.0 $\pm$ 5% @ 6.0 GHz	<.0015	-1200 x 10 <sup>-6</sup>	10.7 x 10 <sup>-6</sup>	0.01	3.85	0.1
MCT-140	140.0 $\pm$ 10% @ 6.0 GHz	<.0015	+1180 x 10 <sup>-6</sup>	10.5 x 10 <sup>-6</sup>	0.01	3.83	0.1

Copyright © 2010, 2016, 2017 Trans-Tech Inc., All Rights Reserved.

Information in this document is provided in connection with Trans-Tech, Inc. ("Trans-Tech"), a wholly-owned subsidiary of Skyworks Solutions, Inc. These materials, including the information contained herein, are provided by Trans-Tech as a service to its customers and may be used for informational purposes only by the customer. Trans-Tech assumes no responsibility for errors or omissions in these materials or the information contained herein. Trans-Tech may change its documentation, products, services, specifications or product descriptions at any time, without notice. Trans-Tech makes no commitment to update the materials or information and shall have no responsibility whatsoever for conflicts, incompatibilities, or other difficulties arising from any future changes.

No license, whether express, implied, by estoppel or otherwise, is granted to any intellectual property rights by this document. Trans-Tech assumes no liability for any materials, products or information provided hereunder, including the sale, distribution, reproduction or use of Trans-Tech products, information or materials, except as may be provided in Trans-Tech Terms and Conditions of Sale.

THE MATERIALS, PRODUCTS, AND INFORMATION ARE PROVIDED "AS IS" WITHOUT WARRANTY OF ANY KIND, WHETHER EXPRESS, IMPLIED, STATUTORY, OR OTHERWISE, INCLUDING FITNESS FOR A PARTICULAR PURPOSE OR USE, MERCHANTABILITY, PERFORMANCE, QUALITY, OR NON-INFRINGEMENT OF ANY INTELLECTUAL PROPERTY RIGHT; ALL SUCH WARRANTIES ARE HEREBY EXPRESSLY DISCLAIMED. TRANS-TECH DOES NOT WARRANT THE ACCURACY OR COMPLETENESS OF THE INFORMATION, TEXT, GRAPHICS, OR OTHER ITEMS CONTAINED WITHIN THESE MATERIALS. TRANS-TECH SHALL NOT BE LIABLE FOR ANY DAMAGES, INCLUDING BUT NOT LIMITED TO ANY SPECIAL, INDIRECT, INCIDENTAL, STATUTORY, OR CONSEQUENTIAL DAMAGES, INCLUDING WITHOUT LIMITATION, LOST REVENUES OR LOST PROFITS THAT MAY RESULT FROM THE USE OF THE MATERIALS OR INFORMATION, WHETHER OR NOT THE RECIPIENT OF MATERIALS HAS BEEN ADVISED OF THE POSSIBILITY OF SUCH DAMAGE.

Trans-Tech products are not intended for use in medical, lifesaving, or life-sustaining applications, or other equipment in which the failure of the Trans-Tech products could lead to personal injury, death, or physical or environmental damage. Trans-Tech customers using or selling Trans-Tech products for use in such applications do so at their own risk and agree to fully indemnify Trans-Tech for any damages resulting from such improper use or sale.

Customers are responsible for their products and applications using Trans-Tech products, which may deviate from published specifications as a result of design defects, errors, or operation of products outside of published parameters or design specifications. Customers should include design and operating safeguards to minimize these and other risks. Trans-Tech assumes no liability for applications assistance, customer product design, or damage to any equipment resulting from the use of Trans-Tech products outside of stated published specifications or parameters.

Skyworks and the Skyworks symbol are trademarks or registered trademarks of Skyworks Solutions, Inc., in the United States and other countries. Third-party brands and names are for identification purposes only, and are the property of their respective owners.